



PLANT PURCHASE SPECIFICATION

JHANSI

PURCHASE SPECIFICATION

No. JS 27197

PREFACE SHEET

REV-05

SILICONE INSULATING LIQUID

FOR INTERNAL USE ONLY
REMOVE THIS PREFACE BEFORE ISSUE TO SUPPLIER

Comparable Standards:- IEC-60836-2005


Probable Suppliers:-

1. Dow Corning
2. Momentive Performance Materials
3. Shin-Etsu

COPYRIGHT AND CONFIDENTIAL

The information on this document is the property of Bharat Heavy Electricals Ltd. Jhansi.
It must not be used directly or indirectly in any way detrimental to the interest of the company.

COPYRIGHT AND CONFIDENTIAL
 The information on this document is the property of Bharat Heavy Electricals Ltd. Jhansi.
 It must not be used directly or indirectly in any way detrimental to the interest of the company.

	PLANT PURCHASE SPECIFICATION JHANSI	PURCHASE SPECIFICATION No. JS 27197
		Page 1 of 3

SILICONE INSULATING LIQUID

1. GENERAL:

This Standard covers the specifications and test methods for unused Silicone Type T-1 transformer liquid (polydimethyl siloxane, without additives) intended for use in transformers.

2. APPLICATION:

For use as dielectric and cooling medium in HVR transformers for ESP.

3. COMPLIANCE WITH NATIONAL/INTERNATIONAL STANDARDS:

IEC-60836: 2005 "Specifications for unused silicone insulating liquids for electro technical purposes" with additional requirement at Cl. no. 6.4.

4. TEST METHOD:

Unless otherwise specified, the tests shall be conducted in accordance with relevant method as per IEC-60836: 2005

5. SAMPLE FOR TEST:

Sampling for test shall be in line with IEC-60475. 5 liters liquid shall be supplied for testing and approval purpose.

6. PROPERTIES:

6.1 APPEARANCE

Shall be clear and free from suspended matter & sediment.

6.2 DENSITY AT 20° C (Kg/dm³)



0.955 - 0.970

6.3 KINEMATIC VISCOSITY

40 ± 4 mm²/s at 40° C

or

50 ± 2.5 cSt at 25° C [as per ASTM D4652]

Revision : 05 DATE : 30/04/16		Reaffirmed DATE : 19/05/22 S.Verma S.Sahay		Issued By: Standard Section, TRE Jhansi	
		Rev-05 issued to add kinematic viscosity at 25°C.		Prepared- N. Varshney 	Approved- B. Naik 



PLANT PURCHASE SPECIFICATION

PURCHASE SPECIFICATION
No. JS 27197

JHANSI

Page 2 of 3

6.4 FLASH POINT (° C)

- a) Pensky Martens Closed cup method : Min. 240
b) Cleveland Open cup method : Min. 300

6.5 FIRE POINT (° C)

Min. 340

6.6 REFRACTIVE INDEX AT 20° C

1.404 ± 0.002

6.7 POUR POINT (° C)

Minus 50 or below

6.8 WATER CONTENT (mg/kg)

(For untreated liquid, as received)

Max 50

6.9 NEUTRALIZATION VALUE (mg KOH/g)

(For untreated liquid, as received)

Max. 0.01

6.10 BREAKDOWN VOLTAGE (kV)

(For untreated liquid, as received)

Min. 40

6.11 DIELECTRIC DISSIPATION FACTOR (DDF) AT 90° C & 50 Hz (For untreated liquid, as received)

Max. 0.001

6.12 PERMITTIVITY AT 90° C

(For untreated liquid, as received)

2.55 ± 0.05

6.13 DC RESISTIVITY AT 90° C (GΩ x m)

(For untreated liquid, as received)

Min. 100

Revision: 05

Issued By: Standard Section, TRE Jhansi



Date: 30th Apr, 2016

Prepared-
N. Varshney

Approved-
B. Naik

COPYRIGHT AND CONFIDENTIAL

The information on this document is the property of Bharat Heavy Electricals Ltd. Jhansi.
It must not be used directly or indirectly in any way detrimental to the interest of the company.

	PLANT PURCHASE SPECIFICATION JHANSI	PURCHASE SPECIFICATION No. JS 27197
		Page 3 of 3
<p>7. <u>TEST REQUIREMENTS:</u></p> <p>Oil samples taken after delivery at any place shall meet all the test requirements stipulated in this specification.</p> <p>8. <u>TEST CERTIFICATE:</u></p> <p>Unless otherwise stated, three copies of test certificate shall be sent along with each consignment giving the following information :-</p> <p>JS-27197 – Silicone Insulating Liquid BHEL P.O. no. Manufacturer's / Supplier's name Batch no. / Lot no. Quantity in liters / number of drums Test values / Certificate of analysis & certificate of compliance for clause 6.</p> <p>9. <u>PACKING AND MARKING:</u></p> <p>Liquid shall be delivered in perfectly clean steel drums of 210 liters nominal capacity with flat or dished fixed ends conforming to Grade-A or Grade-B of IS-1783. Inside surface of the drum to be coated with a suitable coating (e.g. epoxy lacquer, phosphate etc) resistant to insulating oil. Outside surface of drum to be coated with suitable primer and finishing paint or be hot dip galvanized to IS-4759 for protection against atmospheric corrosion. Silicone liquid in 1050 liters IBC containers with steel cage is also acceptable. The drums/container used shall be especially reserved for the purpose. Immediately after filling with oil the drum/container shall be effectively sealed so as to exclude ingress of moisture.</p> <p>The drums / containers shall be indelibly marked with the following information:-</p> <p>JS-27197 – Silicone Insulating Liquid BHEL P.O. no. Manufacturer's / Supplier's name Batch no. / Lot no. Quantity in liters / number of drums/ number of containers</p> <p>10. <u>SHELF LIFE:</u></p> <p>Should be at least 36 months when stored in original sealed container/drum.</p>		
Revision: 05 Date: 30 th Apr, 2016	Issued By: Standard Section, TRE Jhansi	
	Prepared- N. Varshney 	Approved- B. Naik 